

橙色光学玻璃

橙色玻璃特性 (Orange Glass Characteristic)

牌 号 Type	厚度 Thickness (mm)	A[2856K]			D65			化学稳定性 Chemical Stability		N _D	$\alpha \times 10^{-7}$ (/°C)	T _g (°C)	T _s (°C)	S
		x	y	Y	x	y	Y	D _A	D _W					
CB535	2	0.549	0.448	82.2	0.504	0.492	70.2	3	2	1.523	103	527	605	2.64
CB550	2	0.549	0.405	63.6	0.569	0.430	48.4	3	2	1.523	103	527	605	2.64
CB565	2	0.622	0.377	51.6	0.605	0.395	36.7	3	2	1.523	103	527	605	2.64
CB580	2	0.658	0.342	35.9	0.649	0.351	23.3	1	2	1.523	103	527	605	2.64

技术要求
(Technical Indexes)

牌 号 Type	厚度 Thickness (mm)	$\lambda_{tj}(\text{nm})$	$\lambda_o(\text{nm})$	T $\lambda_o(\%)$	K
CB535	2	535±10	650	≥88.7	≥1.2
CB550	2	550±10	650	≥88.7	≥1.2
CB565	2	565±10	650	≥88.7	≥1.2
CB580	2	580±10	680	≥88.7	≥1.2

气泡、条纹、应力级别
(Class Of Bubble, Stripe, Stress)

牌 号 Type	气泡 Bubble	条纹 Stripe	应力 Stress
CB535	C-B	3C	3
CB550	C-B	3C	3
CB565	C-B	3C	3
CB580	C-B	3C	3

