

紫外透射可见吸收光学玻璃

紫外透射可见吸收玻璃特性 (Ultraviolet Glass Characteristic)

牌 号 Type	厚度 Thickness (mm)	A[2856K]			D65			化学稳定性 Chemical Stability		N _D	$\alpha \times 10^{-7}$ (/°C)	T _g (°C)	T _s (°C)	S
		x	y	Y	x	y	Y	D _A	D _W					
ZWB1	1	0.734	0.266	0.1	0.726	0.262	0.0	4	4	1.557	94	529	588	2.87
ZWB2	1	0.532	0.171	0.9	0.231	0.032	0.4	2	2	1.520	97	515	589	2.65
ZWB3	2	0.711	0.256	0.3	0.538	0.176	0.1	2	3	1.526	85	527	616	2.63

技术要求
(Technical Indexes)

牌 号 Type	厚度 Thickness (mm)	254 (nm)	280 (nm)	313 (nm)	334 (nm)	365 (nm)	405 (nm)	700 (nm)		
ZWB1	1		≥ 50.0	≥ 81.0			≤ 1.0	≤ 30.0		
ZWB2	1			≥ 38.0		≥ 80.0	≤ 8.0	≤ 14.0		
ZWB3	2	≥ 50.0			≥ 86.0		≤ 28.8	≤ 64.6		

气泡、条纹、应力类级别
(Class Of Bubble, Stripe, Stress)

牌号 Type	气 泡 Bubble	条 纹 Stripe	应 力 Stress
ZWB1	C	4	4
ZWB2	C	4	3
ZWB3	C	4	4

