紫色光学玻璃

紫色玻璃特性 (Violet Glass Characteristic)

牌 号 T	厚度 Thickness (mm)	A[2856K]			D65			化学稳定性 Chemical Stability		N _D	α x 10 ⁻⁷ (/°C)	T ₉ (℃)	T₅ (°C)	S
		Х	У	Υ	х	У	Y	D _A	D _W		, ,	` '		
ZB1	2	0.519	0.018	0.2	0.160	0.016	0.6	1	3	1.524	29	519	589	2.53
ZB2	2	0.158	0.020	0.2	0.160	0.017	0.7	1	2	1.495	58	551	655	2.40
ZB3	2	0.165	0.011	0.1	0.160	0.010	0.2	1	2	1.495	57	538	636	2.40

技术要求 (Technical Indexes)

 	 	力类级。 Stripe	别 , Stress	5)
	\neg			ı

牌 号 Type	厚度 Thickness (mm)	300 (nm)	360 (nm)	400 (nm)	480 (nm)	700 (nm)	710 (nm)	720 (nm)	800 (nm)	
ZB1	2			≥70.0	≤6.0	≤4.0				
ZB2	2	≥31.0	≥78.2		≤3.7		≤9.2		≥80.4	
ZB3	2	≥18.0	≥78.2		≤0.2			≤10.0	≥80.4	



